



KGT HP011J - Class PE100

KGT HP011J is a natural pipe grade resin which is manufactured by suspension polymerization of ethylene monomer. KGT HP011J is a bi-model high density polyethylene with 1-Butene as co monomer.

Applications

- Top quality PE100 pressure
- Pipes for gas and water transportation at higher pressures or with thinner walls as PE80 (UV stabilization and/ or pigments during processing)

Additives

- Antioxidant/Process stabilizer
- Lubricant (processing aid)/ acid scavenger

Test/Composition	Typical Value	Unit	ASTM Method
Density	0.948	g/ml ³	ISO1183
FRR 21.6/5	28		
Hydrostatic Strength (80°C)	5000 (4.5N/mm ²)	h	ISO1167
MFR190°/21.6	6.2	(g/10 min)	ISO1133
MFR190°/5	0.22	(g/10 min)	ISO1133
Notched Impact (23°C)	24	mJ/mm ²	ISO179/1eA

1. Test specimen from compression moulded sheet at 23°C.
2. FRR values are statistical and calculated by dividing MFR values.
3. Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values.

Al Khuwair, Road No:824, plot No:2914
Office No:2910 · P. O. Box: 511. PC: 400 Muscat- Oman

www.kgtoil.com

Marketing@kgtoil.com